

PRODUCT: DOUBLE SIDED CLOTH TAPE

TEST ITEM	UNIT	TEST RESULT	REMARKS
Adhesive		Hot melt	
Carrier		cloth fiber wz pe	/
Thickness	mm	0.24±0.01mm	GB/T7125-1999
Tack	#	≥12.00	GB4852-84
180oC Peel Adhesion	oz/in	≥45.00	GB/T2792-1998
Tensile strength	KN/m	≥3.0	GB7753-87
Elongation	%	≥15.00	GB7753-87
Otherwise			
<p>Remarks: All the above data are obtained in our lab with T:20℃ RH:60% and can not be the gists to the quality of sample.</p>			